

General technical specifications

PP RECYCLED

Commercial Name		PP RECYCLED		
VALUE	TEST METHOD	RESULT	Test Date	10/06/2017
MFI	ISO 1133 B g/10 min. 2,16Kg.230°	26,00 - 30,00		
DENSITY AT 23 °C	ISO 1183 g/cc	0,905 - 0,917		
CARBON BLACK	ISO 6964	-----		
ASHES	ISO 3451	Max 2%		
COLOURS	VISUAL SEPARATED COLOURS	GREEN, BLUE, RED, YELLOW, WHITE, BLACK		



- . NOT FOR FOOD CONTACT
- . HOMOGENEOUS LOT 22÷25 TN
- . PACKAGING 1.000 KGS BIG BAG

HDPE RECYCLED

Commercial Name		HDPE RECYCLED		
VALUE	TEST METHOD	RESULT	Test Date	07/05/2017
MFI	ISO 1133 g/10 min. 2,16Kg.190°	7,00 ± 3,00		
DENSITY	ISO 1183 g/cc	0.955 (± 0,010)		
CARBON BLACK	ISO 6964	-----		
ASHES	ISO 3451	Max 2%		
COLOURS	VISUAL SEPARATED COLOURS	GREEN, BLUE, RED, YELLOW, WHITE, BLACK		



- . NOT FOR FOOD CONTACT
- . HOMOGENEOUS LOT 22÷25 TN
- . PACKAGING 1.000 KGS BIG BAG